

SYSTEM BENEFITS:

CPD 4210A Resin with CPD 9227B Hardener is a long pot life, thixotropic laminating system for use fabricating large parts. While cure is complete after seven days at room temperature, a moderate post cure will decrease cure time and increase physical property values. The resin system has a convenient 3 to 1 by volume mix ratio for ease of use.

- Laminating
- Extra long gel time
- Thixotropic

HANDLING PROPERTIES

| | CPD 9227B | Test Method |
|--------------------------------------|------------|-------------|
| Resin Density at 25°C, lbs/gal | 9.4 | ASTM D1475 |
| Hardener Density at 25°C, lbs/gal | 8.0 | ASTM D1475 |
| Resin Viscosity at 25°C, cP | 1,450 | ASTM D2196 |
| Hardener Viscosity at 25°C, cP | 40 | ASTM D2196 |
| Mix Ratio by Weight | 100A : 28B | Calculated |
| Mix Ratio by Volume | 3A : 1B | Calculated |
| Initial Mixed Viscosity 25°C, cP | 700 | ASTM D2196 |
| Gel Time at 25°C, 150g mass, minutes | 140 | ASTM D2471 |

PHYSICAL PROPERTIES

| | CPD 9227B | Test Method |
|--------------------------------|-----------|-------------|
| Color | Opaque | Visual |
| Izod Impact, Notched, ft-lb/in | 1.00 | ASTM D256 |
| Tensile Strength, psi | 10,400 | ASTM D638 |
| Tensile Modulus, psi | 425,000 | ASTM D638 |
| Tensile Elongation, % | 6.8 | ASTM D638 |
| HDT, Room Temp Cure, °F | 125 | ASTM D648 |
| HDT, Post Cure, °F | 150 | ASTM D648 |
| Compressive Strength, psi | 14,300 | ASTM D695 |
| Flexural Strength, psi | 17,500 | ASTM D790 |
| Flexural Modulus, psi | 453,000 | ASTM D790 |
| Hardness, Shore D | 84 | ASTM D2240 |
| Linear Shrinkage, in/in | <0.002 | ASTM D2566 |

SYSTEM POST CURE OPTIONS:

Select one of the following cure schedules depending on the available time, the physical properties of the mold and the desired physical properties of the final part. Post cure the part to obtain maximum physical and thermal properties of the system. The recommended post cure temperature ramp rate between stages is up 5°F per minute for heating and down 1-2°F per minute for cooling. Heating and cooling ramp rates can vary based on size and thickness of the part. For larger thicker parts use a more conservative ramp. If you need to deviate from the recommended post cure schedule, please contact our technical service department.

CURE INCREMENTS:

| CPD 9227B | 24 Hours at 77°F (25°C) | 7 Days at 77°F (25°C) | 4 Hours at 120°F (49°C) | 4 Hours at 150°F (66°C) | 2 Hours at 180°F (82°C) | 4 Hours at 180°F (82°C) |
|-------------|-------------------------------|-----------------------------|-------------------------------|-------------------------------|-------------------------------|-------------------------------|
| Post Cure 1 | | Supported | Unsupported | | Unsupported | Unsupported |
| Post Cure 2 | Supported | | | Supported | Unsupported | Unsupported |
| Post Cure 3 | | | | | | |

MIXING AND SURFACE PREP:

Always use the recommended mix ratio for the system. Do not deviate in an attempt to speed up or slow down gel time. Mix together thoroughly, scraping sides and bottom of mixing container, until no streaks or striations are visible, then use immediately. Use only clean dry tools for mixing and applying. Do not mix or apply below 60°F. All surfaces must be clean, dry, and free of any surface contamination. Molds and patterns should be treated with release or parting agents.

STORAGE AND CRYSTALLIZATION:

Store between 60-90°F in a dry place. After use, tightly reseal all containers and store products on a raised surface during cold weather and avoid storing near outside walls or doors. If available, Purge with dry nitrogen to preserve color and minimize moisture contamination. Do not allow to freeze during winter storage. Do not use material with any signs of crystallization such as solid chunks, grainy texture or white color. Crystallization can be reversed by heating the material to 125-140°F, and stirring occasionally, until all crystals dissolve.

SAFETY HANDLING:

Wear protective gloves, clothing, and eye/face protection. Use only outdoors or in a well-ventilated area. Avoid contact to the skin and eyes. Avoid breathing dust, fumes, gas mist, vapors and spray. Wash hands thoroughly after handling. Take off contaminated clothing and wash before reuse. These products may cause skin and respiratory allergic reactions. Consult product Safety Data Sheets for complete precautions for use of this product.

Endurance Technologies, Inc. has experience only in the compounding of resins and hardeners and not in the actual manufacture of tools or parts. Each piece is different. The user should run tests to assure the suitability of the system for use in a particular application. The test data and results set forth herein are based on laboratory work and do not necessarily indicate the results that the buyer or user will attain.

Endurance Technologies, Inc. makes no warranty expressed or implied, including warranties of merchantability or fitness for a particular use. Under no circumstances will Endurance Technologies, Inc. be liable for incidental, consequential or other damages, alleged negligence, breach of warranty, strict liability, tort or any other legal theory arising out of the use or handling of this product.

Revised April 2019